

SITE MIXED SYSTEM

Technical
Information



Nonexplosive-Until-Pumped Bulk Explosives



Product Description

The Dyno Nobel SITE MIXED SYSTEM™ [SMS™] represents the most advanced and economical method to safely deliver high performance, water resistant bulk explosives to the borehole. The SMS Bulk Delivery Truck and the SMS Bulk Emulsion Explosive formulas are the key components of SMS.

The SMS Bulk Delivery Truck is a self-contained, mobile bulk emulsion manufacturing facility which produces SMS Bulk Emulsion explosives and then delivers it to the bottom of the borehole. Only non-explosive ingredients are used!

SMS bulk explosives are high performance, booster sensitive pumpable emulsion explosives specially formulated to be manufactured at the borehole and to match specific blasting requirements at the time of loading. SMS bulk explosives use Dyno Nobel chemical gassing technology to sensitize the emulsion in the borehole and the SITE MIXED SYSTEM provides many choices in explosive loading densities and energies. Refer to the data table at left for the physical properties of typical SMS bulk explosive grades.

Properties

MSDS
#1052

	1116	1136P	1146P	HD
Percent Emulsion	100	70	65	65
Density (g/cc)	1.25	1.25	1.25	1.32
Energy^a (cal/g)	650	725	750	750
(cal/cc)	815	910	940	990
Relative Bulk Strength^a	0.74	0.82	0.85	0.85
Relative Bulk Weight^a	1.13	1.25	1.30	1.37
Velocity^c (m/sec)	5,200	4,600	4,500	4,500
(ft/sec)	17,100	15,100	14,800	14,800
Detonation				
Pressure^c (Kbars)	85	66	63	67
Gas Volume^a (moles/kg)	45.3	44.5	44.3	44.3
Water Resistance	Excellent	Excellent	Excellent	Excellent
Minimum Diameter				
(mm)	75	125	125	150
(in)	3	5	5	6
Loading Method	Pump	Pump	Pump	Pump

^a Borehole density can be varied from 1.10 to 1.32 g/cc to match applications

^b **All Dyno Nobel Inc. energy and gas volume values are calculated using PRODET™**, a computer code developed by Dyno Nobel Inc. for its exclusive use. Other computer codes may give different values.

^c ANFO = 1.00 @ 0.82 g/cc

^d Unconfined @ 150mm (6 in) diameter at average density of 1.25 g/cc.

Hazardous Shipping Description

Oxidizing Substance, Liquid, n.o.s. (Ammonium Nitrate) 5.1 UN 3139 II



SITE MIXED SYSTEM

Technical Information



Application Recommendations

- Emulsion compatible AN prills should be used to manufacture any SMS bulk explosive products.
- The minimum cast booster weight recommended for use as a primer for SMS 1136P, SMS 1146P and SMS HD is 340 gm (12 oz).
- Minimum recommended booster for SMS 1116 is a 150 gm (5 oz) cast booster.
- **ALWAYS** double prime when bulk explosive columns exceed 20 ft. One primer should be positioned near the bottom of the hole and the second nearer the top of the explosive column.
- Do not use detonating cord in borehole diameters less than 178 mm (7 in).
- **NEVER** use SMS emulsion explosives in boreholes deeper than 30 m (100 ft). Where applications require SMS emulsion explosives be used in borehole depths exceeding 100 ft (30m), the conventional alternative (solid density control) to chemical gas sensitization is optional. Before planning an SMS blasting program for deep boreholes, **ALWAYS** contact the Dyno Nobel representative for product recommendations.
- Borehole sleep time is two (2) weeks. Where geology is wet and extended sleep times are anticipated, **ALWAYS** limit ANFO percentage in Dyno Gold LD Heavy ANFO blends to less than 50%. When product will sleep overnight and less water resistant blends are being considered, consult your Dyno Nobel representative for loading recommendations.
- **ALWAYS** use average borehole loading density for blast design and to estimate explosive requirements. Chemically gassed emulsion explosives provide a unique loading density gradient in the borehole with highest density at the bottom and lowest density at the top. Consult the density/depth curves to determine average borehole density.
- Only the Dyno Nobel SMS Bulk Delivery Truck can be used to manufacture Dyno Nobel's SMS emulsion explosives and the SMS Bulk Delivery Truck can be operated only by personnel who have received Dyno Nobel SMS training.

- **ALWAYS** calibrate Dyno Nobel's SMS Bulk Delivery Trucks periodically to ensure emulsion explosive quality and explosive performance. Ensure safety systems are operational before each use.
- Routinely monitor the SMS emulsion explosive density to ensure that equipment remains in calibration during loading,

Transportation, Storage and Handling

- **NEVER** store SMS 1116, 1136P, 1146P and HD. These are bulk, site-mixed booster sensitive emulsion explosives delivered directly into the borehole.
- Transport, store, handle and use SMS ingredients in compliance with federal, state, provincial and local laws governing bulk hazardous materials.

Product Disclaimer Dyno Nobel Inc. and its subsidiaries disclaim any warranties with respect to this product, the safety or suitability thereof, or the results to be obtained, whether express or implied, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AND/OR OTHER WARRANTY. Buyers and users assume all risk, responsibility and liability whatsoever from any and all injuries (including death), losses, or damages to persons or property arising from the use of this product. Under no circumstances shall Dyno Nobel Inc. or any of its subsidiaries be liable for special, consequential or incidental damages or for anticipated loss of profits.

Dyno Nobel Inc.

2795 East Cottonwood Parkway, Suite 500, Salt Lake City, Utah 84121 USA
Phone 800-732-7534 Fax 801-328-6452 Web www.dynonobel.com

DYNO
Dyno Nobel

Groundbreaking Performance