TECHNICAL DATA SHEET

EXPLOS, ZES

TITAN® XL 5000 / 5000 ΔE

Gassed Bulk Emulsion

Prope	rties		SDS #10521
Density	(g/cc) avg The average loading density car 1.3 g/cc to best match rock type *Actual number depends on hole	e and application requirements.	
Energy ^a	(cal/g)	590 - 680	
	(cal/cc)	530 - 885	
Relative Weight Strength ^{a,b}		0.67 - 0.77	
Relative Bulk Strength ^{a,b}		0.74 - 1.23	
Velocity ^c	(m/sec)	3,800 - 7,000	
	(ft/sec)	12,500 - 23,000	
Detonation Pressure (Kbars)		33 - 160	
Gas Volume ^a (moles/kg)		45.0	
Water Resistance		Excellent	
Minimum Diameter (mm)		65	
	(inches)	2.5	
Loading Method		Pumped	

- a All Dyno Nobel Inc. energy and gas volume values are calculated using PRODET™, a computer code developed by Dyno Nobel Inc. for its exclusive use. Other computer codes may give different values.
- b ANFO = 1.00 @ 0.82 g/cc
- ^c Confined in 150 mm (6 in) diameter at average density.

Hazardous Shipping Description

 TITAN XL 5000 is made from TITAN 1000 G bulk emulsion matrix. Refer to the TITAN 1000 G Technical Information Sheet for Hazardous Shipping Description information.

PRODUCT DESCRIPTION

TITAN XL 5000 / 5000ΔE is a gassed, bulk emulsion made from TITAN 1000 G specifically designed for open pit mining operations with reactive ground. This base emulsion is transported as an un-sensitized emulsion. TITAN XL 5000 / 5000ΔE is formulated to inhibit sulfide-bearing ore bodies utilizing Dyno Nobel's patented DIFFERENTIAL ENERGY[™] delivery systems. The product is sensitized during the blast hole loading process using Dyno Nobel's innovative chemical gassing and emulsion processing technology. The process used to manufacture TITAN XL 5000 / 5000ΔE enhances water resistance and detonation performance while improving loading characteristics. Chemical gassing allows the average density of TITAN XL 5000 / 5000ΔE to be varied as required to optimize its explosive performance for best blasting results.





APPLICATION RECOMMENDATIONS

- The minimum cast booster size recommended to prime is the TROJAN® Shield® S.
- TITAN XL 5000 / 5000ΔE can be used in boreholes up to 36 m (150 ft) deep.
- ALWAYS double prime when bulk explosive columns exceed 6 m (20 ft). One primer should be positioned near the bottom of the hole and the second near the collar.
- ALWAYS ensure primers are securely positioned in the explosive column.
- Do not use low grain detonating cord as downlines with TITAN XL 5000 / 5000∆E without first consulting your Dyno Nobel representative.



Product Disclaimer: Please see reverse side.

TECHNICAL DATA SHEET



TITAN® XL 5000 / 5000 ΔE

Gassed Bulk Emulsion

TRANSPORTATION, STORAGE AND HANDLING

- TITAN XL 5000 / 5000ΔE's base emulsion TITAN 1000 G can be stored for 3 months at temperatures between -18° C and 32° C (0° F and 90° F). Older product should be used first and all storage tanks should be kept clean of residual product.
- Use only pumps which have been approved by Dyno Nobel for 5.1 emulsion matrix transfer. Pump type, pump speed, worn pump parts, repeated repumping and pumping against high hose pressures can increase TITAN 1000 G viscosity and decrease shelf life.
- · ALWAYS monitor emulsion pump performance and check pumps periodically for excessively worn parts. Design storage facilities to minimize repeated pumping.
- Transport, store, handle and use TITAN emulsions in compliance with federal, state, provincial and local laws governing bulk oxidizing liquids.

ADDITIONAL INFORMATION – Visit dynonobel.com for Brochures and Case Studies related to this product.

Dyno Nobel